

PART 1 GENERAL**1.1 Summary**

- .1 Unless otherwise indicated, follow the standards below when specifying exterior painting for landscape use. These standards are not intended to restrict or replace professional judgment.

1.2 References

- .1 American Society for Testing and Materials (ASTM)
 - .1 ASMT B117 Standard Practice for Operating Salt Spray (Fog) Apparatus.
 - .2 ASTM D2247 Standard Practice for Testing Water Resistance of Coating in 100% Relative Humidity.
 - .3 ASTM D3359 Standard Test Methods of Measuring Adhesion by Tape Test.

1.3 Design Requirements

- .1 McGill does not have design requirements with regards to exterior painting for landscape uses.

PART 2 PRODUCTS**2.1 General**

- .1 Powder Coated Paint
 - .1 Polyester powder paint with zinc enriched primer with final thickness of 7 to 8 mils. The material used is polyester resin for external use and resistant to UV rays. This resin is stabilized by controlled temperature cooking.
 - .2 Conforming to the ASTM B117, ASTM D2247 and ASTM D3359 standards.
 - .3 Type: Tiger Drylac 49/76107 SMOOTH SEMI-GLOSS, or approved equivalent.
 - .4 Colour : RAL #7016, unless otherwise indicated for specific works in other sections.

END OF SECTION